

BASE OIL ETRO3

TESTS	METHOD	UNIT	SPEC	RESULTS
Appearance	Visual	-	Bright & Clear	Bright & Clear
Density @ 15°C	ASTM D4052	kg/L	Report	0.8298
Color	ASTM D1500	-	0.5 Max	L 0.5 ASTM Color
Kinematic Viscosity @ 40°C	ASTM D445	mm ² /s (cSt)	9.0 Min	10.010
Kinematic Viscosity @ 100°C	ASTM D445	mm ² /s (cSt)	2.7 – 3.2	2.728
Viscosity Index	ASTM D2270	-	Report	114
Pour Point	ASTM D5950	°C	- 27 Max	- 39
Flash Point	ASTM D92	°C	170 Min	185
Sulfur Content	ASTM D2622	mg/kg (ppm wt)	Report	< 3
Saturates	ASTM D7419	wt%	Report	99.4