

## BO LUBO 150N

Test Items	Test Method	Limit	Test Results
			520D160
ASTM color	ASTM D1500	Max 0.5	L0.5
Viscosity @ 40 Deg C, mm2/s	ASTM D445	Report	29.080
Viscosity @ 100 Deg C, mm2/s	ASTM D445	5.0-5.5	5.268
Viscosity index	ASTM D2270	Min 100	114
Pour point	ASTM D6749	Max -12	-22
Flash point, CoC, C,	ASTM D92	Min 200	228
Aromatics, %	ASTM D3238	Max 1.0	0.0
CCR, wt%	ASTM D189	Max 0.01	L0.01
TAN, mgKOH/g	ASTM D974	Max 0.01	0.006

Remark: