

BO LUBO 600N

The followings are the results of analysis performed by GSC on the sample of shore tank(s) before loading.

Test Items	Test Method	Limit	Test Results
ASTM color	ASTM D 1500	MAX 0.5	L0.5
Viscosity, @40°C, cSt	ASTM D 445	REPORT	107.400
Viscosity, @100°C, cSt	ASTM D 445	12.0-12.9	12.100
Viscosity Index	ASTM D 2270	MIN 95	102
Pour Point °C	ASTM D 6749	MAX -12	-18
Flash point, °C	ASTM D 92	MIN 246	272
Aromatics, wt%	ASTM D 3238	MAX 1.0	0.0
CCR, wt%	ASTM D 189	MAX 0.01	L0.01
TAN, mg KOH/g	ASTM D 974	MAX 0.01	0.006

Remark: